

Technical Data Sheet

Dekwall

Dimensions Available			600x300x3mm	
	Standard - Test Method	Unit	Result	
			Wax	Varnish
Dimensions	EN 427	mm	600 ± 0.5% 300 ± 0.5%	
Squareness	EN 427	mm	600: < 1.0mm 300: < 0.5mm	
Thickness	ISSO 7322	mm	3.0 ± 0.3%	
Apparent density	EN 672	Kg/m ³	≥ 200	
Dimension stability	EN 434	%	≤ 0.4	
Curling	EN 434	mm	≤ 6	
Moisture content	EN 12105	%	≤ 7	
Formaldehyde	EN 12149, method C	mg/Kg	≤ 95	
Vinyl Chloride Monomer (VCM)	EN 12149, TEST B	mg/Kg	≤ 0.2	
Thermal resistance	EN 12667	m ² K/w	0.0583	0.0572
Reaction to Fire	EN 13501-1	Class	E _{gr} , d0	D _{s1} , d0
Sound Absorption	ISO 354	α_w	0.10	
Release of heavy metals and specific elements	EN 12149		fulfilled	

www.wicanders.com

